

2K Urethane Sealer

4:1:1

2.1 VOC when mixed 4:1

Part Numbers:

#6401-1 Grey 1 Gallon

#6402-1 White 1 Gallon

#6403-1 Black 1 Gallon

Products Needed:

6501-4 Primer Activator.

870, 885 or 895 Urethane Reducer.

O-VOC Reducers may be used in 2.1 VOC compliant areas.

Mixing:

4:1:1

Prepping:

One wet coat of this sealer mixed 4:1:1 will fill 320 dry sand scratches however we recommend first preparing the area with 400-600 grit before spraying sealer.

Spraying:

Spray one wet coat of sealer over the properly prepped area and let it set for 10 minutes to 4 hours before applying color. After 4 hours the sealer must be sanded. To fix imperfections after spraying sealer it may be sanded in 15-30 minutes depending on temperature and grade of reducer used. It's very important to use the proper grade/speed urethane reducer. On large areas we recommend using the slowest speed reducer possible.

As a Primer:

This product can be used as a 2K Primer by mixing it 4:1 and without reducer.